



**PROTECTIVE
&
MARINE
COATINGS**

**Acrydur BC01
PRODUCT TECHNICAL DATA**

PRODUCT DESCRIPTION

Acrydur BC01 is a solvent free, medium viscosity Methyl Methacrylate (MMA) based slightly elasticized body coat used as trowelling mortar binder by adding fillers such as sand or coloured quartz. Different levels of fillers can be used to make either a trowel applied screed or a self-levelling flooring system, both suitable for heavy load impact. The self-levelling system can be scattered with further aggregate to build up a textured finish. Acrydur BC01 systems are then usually sealed with an Acrydur coloured or clear topcoat as required.

ADVANTAGES

- Rapid curing
- Used as a binder for screeds or self-levellers
- Very hard wearing
- Excellent bond to substrate
- Easy to apply

RECOMMENDED USE

- As a body coat screed or self-leveller for Acrydur flooring systems

PRODUCT DATA

Colours:	Clear	Application at 20°C
Finish:	N/A	Hardening time: Approximately 30 minutes or once surface has lost tackiness
Flash Point:	+ 10°C	Pot Life: 10 minutes from mixing
Cleanser/Thinner:	N/A	<i>The amount of material to be prepared for application should be calculated. Do not prepare more material than what can be applied correctly within the pot life.</i>
Pack Size:	25 kg, 190kg	<i>All mixed products must be used within the pot life time limit, if the product is left in the container after mixing and not used, it may release hazardous fumes due to exothermic reaction.</i>
Mixing Ratio:	The base requires 2-6% hardening powder depending on site conditions	Coverage Rate: Typically 2 kg/m ² (Theoretical)
Density:	Approximately 0.99 g/cm ³	<i>Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.</i>
Shelf Life:	12 months when stored in unopened containers	System Thickness: 2 - 3 mm or 4 – 6 mm
Storage:	Keep out of direct sunlight. Store in a dry place, between 15°C – 20°C	<i>The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application may vary.</i>
Recommended Application Methods:	Trowel and squeegee	



Acrydur BC01

SURFACE PREPARATION

New Concrete Floors: New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and making sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using **Acrydur RM01 and Acrydur RM02**.

Existing Floors (previously coated): All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with the existing floor coating. Where **Acrydur BC01** is applied to concrete surfaces, care must be taken to ensure that surface preparation is thorough but does not disfigure the surface.

PRIMING

Substrates should be primed prior to the application of an **Acrydur BC01** body coat. **Acrydur PR02** is for priming substrates prior to the application of **Acrydur** flooring systems. **Acrydur PR01** can also be used as a primer. Porous substrates may require double priming. The primer application should be lightly scattered with sand (approximately 0.3 – 0.8 mm in size) at an approximate rate of 0.3 kg/m².

Acrydur BC01 is supplied in pails or drums. Before mixing ideally precondition the **Acrydur** resin and the **Peroxide** as well as the fillers and quartz components to a temperature of approximately 15 °C to 20°C.

The application temperature should be 0°C to 35°C throughout the application and the curing period.

MIXING AND APPLICATION

Prior to use, stir the **Acrydur** to obtain an even distribution of the paraffin contained in the product. With pourable mixes, the **Peroxide** is the last component to be added in the mix. For mortars, add the **Peroxide** prior to adding the aggregate. Pour the appropriate ratio of hardening powder into the container of resin (see table below). Mix until the **Peroxide** is completely dissolved.

Hardener addition % guidance

Temperature	Hardening powder	Pot life / minutes	Hardening time
+ 0 °C	6%	20	60
+ 10 °C	4%	20	45
+ 20 °C	3%	15	30
+ 30 °C	2%	10	25

NB: The quantity of hardening powder is always related to the amount of resin

Hardening powder must not be added to the reactive resin and resin/filler mix until immediately before application. In the case of pourable mixes, the hardener should be the last component added, while for mortars or very thixotropic resins the full amount of filler or thixotropic agent should be stirred in first. The hardening powder must always be stirred in and allowed to dissolve in the corresponding mixture or the pure resin. The stirring time will depend on the type and the condition of the mixing equipment used and on the temperature of the material.

APPLICATION CONDITIONS

Acrydur BC01 should be spread coarsely to the desired thickness using a trowel or squeegee and then should be compressed and smoothed using a large smoothing trowel so that no pores and trowel marks remain in the floor.

The application of the system requires consistent and even technique to ensure the prevention of puddles and good compaction of the mix and to avoid pores and air bubbles within the stated tolerance of fillers and resin and depending on the thickness of the application.

In case of coatings and floors in areas between metal profiles and inlets, we recommend that elastic joints with the same decorative look being applied in the transition area. Otherwise, temperature stresses could lead to forming of small cracks at the contact zone.

See *Sherwin-Williams Acrydur System Guides for recommended floor systems*

TECHNICAL INFORMATION

The following figures are obtained from laboratory tests and our experience with this product.

Category Guide:	FerFA Category 2/3/4/5
Compressive Strength: (DIN 1164)	38 N/mm ² (4-6mm thickness Coloured quartz screed)
Tensile Strength: (DIN 1164)	23 N/mm ² (4-6mm thickness Coloured quartz screed)
Bond Strength:	>1.5 MPa (Substrate failure)
Water penetration:	Impervious

WARRANTY	DISCLAIMER
<p><i>Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.</i></p> <p><i>The information detailed in this datasheet is liable to modification from time to time in the light of experience and normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.</i></p>	<p><i>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.</i></p>
HEALTH AND SAFETY	
<p><i>Consult Product Health and Safety Datasheet for information on safe storage, handling and application of this product.</i></p>	

www.sherwin-williams.com/protective EMEA1

This datasheet is specifically subject to the disclaimer which can be found at: <http://protectiveemea.sherwin-williams.com/Home/Disclaimer>