



**PROTECTIVE
&
MARINE
COATINGS**

**Elladur SF Clear
PRODUCT TECHNICAL DATA**

PRODUCT DESCRIPTION

Elladur™ SF Clear is a high-build Polyaspartic/Polyurea type fast-cure floor coating system based on advanced materials, designed to provide a transparent tough and durable gloss finish to a range of floor surfaces. Elladur™ SF Clear is light stable and taint approved with good chemical resistance. Decorative and anti-slip finishes can also be created incorporating suitable flakes and aggregates.

ADVANTAGES

- Fast curing at low temperature
- High build
- Tough but flexible
- UV stable
- Ease of application
- Excellent high gloss finish
- Excellent adhesion
- Solvent free

RECOMMENDED USE

- Where high build UV stable coatings are required
- Areas where a fast return to service is required
- Medical, Commercial and Industrial Floor areas
- Decorative floors
- Domestic areas

PRODUCT DATA

<p>Volume Solids: ~100%</p> <p>VOC: <12 g/l calculated per full mixed unit</p> <p>Colours: Clear</p> <p>Finish: Smooth gloss</p> <p>Flash Point: N/A</p> <p>Cleanser/Thinner: N/A</p> <p>Pack Size: 5 kg</p> <p>Mixing Ratio: 1.8 parts base to 1 part hardener by weight only</p> <p>Pack Weights: 3.25kg base/1.75kg hardener</p> <p>Mixed Density: Approximately 1.08 g/cm³</p> <p>Shelf Life: 12 Months (Base & Hardener)</p> <p>Storage: Keep out of direct sunlight. Store in a dry place, between 15°C – 30°C</p> <p>Recommended Application Methods: Brush, roller or squeegee</p>	<p>Application at 20°C</p> <p>Recoating Intervals: 3 - 4 hours or once surface has lost tackiness (maximum 8 hours)</p> <p>Light Traffic: 5 – 6 hours</p> <p>Full Traffic: 8 – 10 hours</p> <p>Full Chemical Cure 7 days</p> <p>Pot Life: 20 – 30 minutes from mixing, based on 5 kg pack size</p> <p><i>The pot life may be shorter for larger pack sizes if the paint is not used within the pot life limit.</i></p> <p>Note: All mixed paint must be used within the pot life time limit, if the paint is left in the container after mixing and not used, it may release hazardous fumes due to exothermic reaction.</p> <p>Coverage Rate: 5 kg will cover 30 m² @ 150 µm WFT (Theoretical) <i>Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.</i></p> <p>System Thickness: (Recommended) 150 – 250 µm</p> <p><i>The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application may vary.</i></p>
-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------



Elladur SF Clear PRODUCT TECHNICAL DATA

SURFACE PREPARATION

New Concrete Floors: New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and making sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using **Resuscreed PA**.

Existing Floors (previously coated): All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with the existing floor coating. Where **Elladur SF Clear** is applied to masonry/concrete surfaces, care must be taken to ensure that surface preparation is thorough but does not disfigure the surface.

PRIMING

See Sherwin-Williams System Sheets for recommended floor systems.
Open and porous substrates may require priming with **Resuseal WB**, also **Resuprime ST** may be used as primer on the dry substrates only with less than 75% ERH reading.

Where the Relative Humidity of a substrate exceeds 75% ERH please refer to the table below for required number of coats to achieve proper moisture tolerance.

ERH%	Required Coating Thickness
75-85	1 coat of Resuprime MVT at 200 µm per coat
85-92	2 coats of Resuprime MVT at 200 µm per coat
92-97	3 coats of Resuprime MVT at 200 µm per coat

For further information please refer to recommended individual product data sheets.

APPLICATION CONDITIONS

The ambient temperatures of the areas should not be allowed to fall below 15°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 10°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to the installation.

Substrate Temperature: 2 - 30°C

Note: Use brushes or rubber squeegee to spread the coating and then back roll it if required to achieve proper coverage rate.

Relative Humidity up to 90%

In case of application at lower temperature, DO NOT store the material in cold conditions as it will affect the material viscosity and flow. Make sure materials are kept at specified storage condition prior to application.

APPLICATION

Mixing: Mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two to three minutes until the two components are fully combined. The mixed unit should be applied immediately by roller, brush or squeegee with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

Elladur™ SF Clear may be applied to an existing resin floor system where a primer is not required. When applied direct to porous substrates such as concrete the surface must be primed with **Elladur™ SF Clear** to ensure good adhesion to the surface.

TECHNICAL INFORMATION

The following figures are obtained from laboratory tests and our experience with this product.

FeRFA Category:	Category 2
Temperature Resistance:	Tolerant of temperatures up to 60°C
Abrasion Resistance: (ASTM D4060-14)	60mg loss per 1000 cycles
Bond Strength: (BS EN 13892-8:2002)	>3 N/mm ² (Substrate failure)

WARRANTY

Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.

The information detailed in this datasheet is liable to modification from time to time in the light of experience and normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

HEALTH AND SAFETY

Consult Product Health and Safety Datasheet for information on safe storage, handling and application of this product.

Sherwin-Williams Protective & Marine Coatings, Tower Works, Kestor Street, Bolton, Lancashire BL2 2AL United Kingdom

T: 01204 521 771 E: sales.uk@sherwin.com www.resinflooring.sherwin.eu

Registered in England 1659941 VAT GB 373 485624

www.sherwin-williams.com/protectiveEMEA

This datasheet is specifically subject to the disclaimer which can be found at: <http://protectiveemea.sherwin-williams.com/Home/Disclaimer>